



SABIC® PP 579S

PP homopolymer for Injection moulding

Description:

This grade has been specially developed for use in thin-walled, antistatic containers. The material has outstanding flow properties and a high stiffness, enabling high production rates. Special characteristics are low tendency for warpage, high lot to lot consistency, good contact transparency and high gloss. It is formulated with a combined processing and antistatic additive package.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical/ medical applications.


This grade material is UL registered under File E111275 (www.ul.com)

IMDS ID: 7172624

Typical values

Revision 20110418

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR) at 230 °C and 2.16 kg at 230 °C and 5 kg	g/10 min g/10 min	47 158	ISO 1133
Density	kg/m ³	905	ISO 1183
Mechanical properties			
Tensile test stress at yield stress at break strain at break	MPa MPa %	41 22 500	ISO 527
Flexural test Flexural modulus	MPa	1900	ASTM D 790
Izod impact notched at 23 °C	kJ/m ²	2.0	ISO 180/4A
Charpy impact notched at 23 °C	kJ/m ²	2.0	ISO 179
Hardness Shore D	-	72	ISO 868
Thermal properties			
Heat deflection temperature at 1.80 MPa (HDT/A) at 0.45 MPa (HDT/B)	°C °C	56 108	ISO 75/A ISO 75/B
Vicat softening temperature at 10 N (VST/A) at 50 N (VST/B)	°C °C	152 90	ISO 306/A ISO 306/B



SABIC® PP 579S

PP homopolymer for Injection moulding

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50 °C) and /or high humidity as this could well speed up alteration and consequently loss of quality of the material and /or its packaging. Keep material completely dry for good processing.

Disclaimer. The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us.

Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.